

FPB

WET-LAD POLYESTER CELLULOSE

MATERIAL
SPECIFICATIONS

FPB 1.0

| | |
|-----------------------|-----|
| BASIS WEIGHT (O.S.Y.) | 1.0 |
| MULLEN BURST (PSI) | 33 |
| TENSILE STRENGTH | — |
| MACHINE DIRECT | 42 |
| CROSS DIRECT | 20 |
| AIR POROSITY (CFM) | 580 |
| NOMINAL MICRON RATING | 40 |

FPB 1.5

| | |
|-----------------------|-----|
| BASIS WEIGHT (O.S.Y.) | 1.5 |
| MULLEN BURST (PSI) | 53 |
| TENSILE STRENGTH | — |
| MACHINE DIRECT | 56 |
| CROSS DIRECT | 30 |
| AIR POROSITY (CFM) | 400 |
| NOMINAL MICRON RATING | 20 |

FPB 1.8

| | |
|-----------------------|-----|
| BASIS WEIGHT (O.S.Y.) | 1.8 |
| MULLEN BURST (PSI) | 58 |
| TENSILE STRENGTH | — |
| MACHINE DIRECT | 70 |
| CROSS DIRECT | 35 |
| AIR POROSITY (CFM) | 330 |
| NOMINAL MICRON RATING | 10 |

FPB 2.3

| | |
|-----------------------|-----|
| BASIS WEIGHT (O.S.Y.) | 2.3 |
| MULLEN BURST (PSI) | 74 |
| TENSILE STRENGTH | — |
| MACHINE DIRECT | 75 |
| CROSS DIRECT | 50 |
| AIR POROSITY (CFM) | 230 |
| NOMINAL MICRON RATING | 5 |

FPB 3.5

| | |
|-----------------------|-----|
| BASIS WEIGHT (O.S.Y.) | 3.5 |
| MULLEN BURST (PSI) | 120 |
| TENSILE STRENGTH | — |
| MACHINE DIRECT | 100 |
| CROSS DIRECT | 75 |
| AIR POROSITY (CFM) | 160 |
| NOMINAL MICRON RATING | 2 |



QUALITY NON-WOVEN PRODUCTS. FOR OVER 30 YEARS.

13033 FAIRLANE LIVONIA, MI 48150

PH: (734) 455-7655 FAX: (734) 455-2460