

LPPS

LAYERED POLYPROPYLENE

MATERIAL
SPECIFICATIONS

LPPS 1.0

BASIS WEIGHT (O.S.Y.)	1.0
MULLEN BURST (PSI)	32
TENSILE STRENGTH	—
MACHINE DIRECT	44
CROSS DIRECT	36
AIR POROSITY (CFM)	351
NOMINAL MICRON RATING	70

LPPS 1.5

BASIS WEIGHT (O.S.Y.)	1.5
MULLEN BURST (PSI)	44
TENSILE STRENGTH	—
MACHINE DIRECT	63
CROSS DIRECT	50
AIR POROSITY (CFM)	269
NOMINAL MICRON RATING	50

LPPS 2.0

BASIS WEIGHT (O.S.Y.)	2.0
MULLEN BURST (PSI)	56
TENSILE STRENGTH	—
MACHINE DIRECT	84
CROSS DIRECT	66
AIR POROSITY	214
NOMINAL MICRON RATING	30

LPPS 2.5

BASIS WEIGHT (O.S.Y.)	2.5
MULLEN BURST (PSI)	68
TENSILE STRENGTH	—
MACHINE DIRECT	104
CROSS DIRECT	82
AIR POROSITY (CFM)	122
NOMINAL MICRON RATING	15



QUALITY NON-WOVEN PRODUCTS. FOR OVER 30 YEARS.

13033 FAIRLANE LIVONIA, MI 48150

PH: (734) 455-7655 FAX: (734) 455-2460