

SPP

SPUN-BOND POLYPROPYLENE

MATERIAL
SPECIFICATIONS

SPP 1.0

BASIS WEIGHT (O.S.Y.)	1.0
MULLEN BURST (PSI)	30
TENSILE STRENGTH	—
MACHINE DIRECT	23
CROSS DIRECT	19
AIR POROSITY (CFM)	605
NOMINAL MICRON RATING	40

SPP 1.5

BASIS WEIGHT (O.S.Y.)	1.5
MULLEN BURST (PSI)	49
TENSILE STRENGTH	—
MACHINE DIRECT	33
CROSS DIRECT	26
AIR POROSITY (CFM)	295
NOMINAL MICRON RATING	20

SPP 2.0

BASIS WEIGHT (O.S.Y.)	2
MULLEN BURST (PSI)	64
TENSILE STRENGTH	—
MACHINE DIRECT	44
CROSS DIRECT	38
AIR POROSITY	205
NOMINAL MICRON RATING	15



QUALITY NON-WOVEN PRODUCTS. FOR OVER 30 YEARS.

13033 FAIRLANE LIVONIA, MI 48150

PH: (734) 455-7655 FAX: (734) 455-2460