

CPR

LAYERED POLYESTER

MATERIAL SPECIFICATIONS

CPR 1.0

BASIS WEIGHT (O.S.Y.)	1.0
MULLEN BURST (PSI)	27
TENSILE STRENGTH	—
MACHINE DIRECT	29
CROSS DIRECT	24
AIR POROSITY (CFM)	786
NOMINAL MICRON RATING	70

CPR 1.5

BASIS WEIGHT (O.S.Y.)	1.5
MULLEN BURST (PSI)	36
TENSILE STRENGTH	—
MACHINE DIRECT	49
CROSS DIRECT	33
AIR POROSITY (CFM)	645
NOMINAL MICRON RATING	50

CPR 2.0

BASIS WEIGHT (O.S.Y.)	2.0
MULLEN BURST (PSI)	63
TENSILE STRENGTH	—
MACHINE DIRECT	76
CROSS DIRECT	39
AIR POROSITY	469
NOMINAL MICRON RATING	40

CPR 2.5

BASIS WEIGHT (O.S.Y.)	2.5
MULLEN BURST (PSI)	66
TENSILE STRENGTH	—
MACHINE DIRECT	92
CROSS DIRECT	44
AIR POROSITY (CFM)	398
NOMINAL MICRON RATING	20



QUALITY NON-WOVEN PRODUCTS. FOR OVER 30 YEARS.

13033 FAIRLANE LIVONIA, MI 48150

PH: (734) 455-7655 FAX: (734) 455-2460